

## CSSPSA S

CHEMSTIK®

Saint-Gobain Tape Solutions

North America | South America | Europe | Asia

For a full list of locations, please visit  
[tapesolutions.saint-gobain.com/contact-us](https://tapesolutions.saint-gobain.com/contact-us)

## CSSPSA S\*

The **Chemstik®** CSSPSA S range of fabrics comprises high quality skived PTFE coated with silicone pressure sensitive adhesive. It provides the unique characteristics of PTFE in a form suitable for application as a surface liner to wood, metal or plastic. A separate liner is applied to the adhesive surface for ease of application.

CSSPSA S liners have excellent release properties and are unaffected by most chemicals and solvents.

## Typical Properties

Property	SPSA-3 S	SPSA-5 S	SPSA-10 S	SPSA-20 S	Test Method
Weight (g/m <sup>2</sup> )	170	280	540	1080	FTMS 191A-5041
Thickness (mm)	0.080	0.130	0.250	0.500	FTMS 191A-5030
Adhesive Thickness (mm)	0.045	0.045	0.045	0.045	FTMS 191A-5030
Tensile Strength (N/cm)	35	53	96	184	FTMS 191A-5102
Minimum Elongation (%)	200	200	200	200	FTMS 191A-5102
Peel Adhesion (N/cm)	5.4	5.6	5.9	6.8	ASTM D3330-83
Polyken Tack (g)	600	550	420	550	-
Standard Widths (mm)	990	1000	1000	1000	-
Temperature Range (°C)	-73 to +260	-73 to +260	-73 to +260	-73 to +260	-

**IMPORTANT:** It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

**WARRANTY:** For a period of 6 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1312EU | © Saint-Gobain (April 2019) | **Chemstik** is a trademark of Saint-Gobain.

