

**TCK105**

TCK105 is a CHEMFAB® PTFE-coated Kevlar® fabric with extremely high tensile strength relative to thickness.

TCK105 is typically used in conveyor belt applications and is particularly suitable as an edge reinforcement material. Kevlar® is recommended for use in moist and/or steam environments.

**Typical Properties**

Property	Value	Value	Test Method
Weight	g/m <sup>2</sup>	220	FTMS 191A-5041
Thickness	mm	0.130	FTMS 191A-5030
Tensile Strength	N/cm	240 x 300	FTMS 191A-5102
Trap Tear Strength	N	30 x 40	FTMS 191A-5136
PTFE Content	%	74	-
Temperature Resistance	°C	-73 to +220	-
Standard Width	mm	1250	-

**Saint-Gobain Performance Plastics Ireland**

Kilrush Business Park,  
Kilrush, Co. Clare, V15 NW27  
Tel: +353 65 90 80 170

**Saint-Gobain Performance Plastics Germany**

Tel: +49 (0) 2203 956-362

**Saint-Gobain Performance Plastics Tygaflor Ltd United Kingdom**

Tel: +44 (0) 1706 746900

**Saint-Gobain Performance Plastics Poland**

Tel: +48 (63) 261 7252

[chemfab@saint-gobain.com](mailto:chemfab@saint-gobain.com)

[www.chemfab.com](http://www.chemfab.com)

Kevlar is a registered trademark of the DuPont Company  
CHEMFAB® is a registered trademark ©2017 Saint-Gobain Performance Plastics Corporation

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof.

Saint-Gobain Performance Plastics does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s). Nothing in this disclaimer limits Saint-Gobain Performance Plastics' liability for death or personal injury due to its negligence

Valid 03/2017 • Supersedes all previous versions  
PDS.CFTCK105.0317.EU.CFMC

